




PRODUCT TECHNICAL DATA SHEET

TECHNICAL DATA SHEET NO.:10012002	DATE: 12.06.2008
MANUFACTURER: ECOPIEDRA, S.L	PRESENTATION: CAJA DE 0,6m ²
CITY: LOECHES	



DESIGNATION OF THE MODEL:	LAJA MARRÓN TIERRA STANDARD
MASS COLOURING:	MARRÓN TIERRA
THICKNESS:	Entre 25 y 55mm
NOMINAL DIMENSIONS:	200x100mm

TECHNICAL CHARACTERISTICS	TEST METHOD	VALUES GUARANTEED BY THE MANUFACTURER	TOLERANCES
Appearance and colour.			
Changes in design colour.	Visual	Not accepted	--
Changes in design appearance of the face.	Visual	Not accepted	--
Dimensional characteristics.			
Length of flat pieces.	UNE EN 14617-16	200,0	± 5 mm
Width of flat pieces.	UNE EN 14617-16	100,0	± 5 mm
Thickness of flat pieces.	UNE EN 14617-16	55,0	± 5 mm
Physical Characteristics.			
Water absorption.	UNE EN 14617-1	12,2	12 ± 2 %
Apparent density.	UNE EN 14617-1	1600	Kg/m ³
Efflorescence*.	UNE 67029 ECO-PE-08	Non - Efflorescent	--
Mechanical characteristics.			
Durability (Frost susceptibility).	UNE EN 14617-5	Non – Frost Susceptibility (NFS)	--
Compressive strength.	UNE EN 1015-11	28,0	± 2 MPa
Flexural strength	UNE EN 14617-2 ECO-PE-10	6,2	± 1 MPa
Thermal shock resistance.	UNE EN 14617-6	No changes in appearance of the face	--
Adherence*.	UNE EN 1348	> 1,0	± 0,5 MPa
Adherence**.	UNE EN 1015-12	No applicable	--
TECHNICAL BUILDING CODE			
Fire resistance.	EN ISO 1716:02 EN ISO 1182:02	CLASE A1*	CLASE A1*
Acoustic insulation.	UNE EN ISO 140-3 UNE EN ISO 140-16	5 - 24	dB
Thermal resistance (R) Thermal conductivity (λ) Transmittance (U)	UNE EN 12667:02	0,05-0,10 0,376 20,00-10,00	m ² .K/W W/m. K W/m ² .K

* Adhesive Cement recommended by ECOPIEDRA, S.L.

** Mortar for Joints recommended by ECOPIEDRA, S.L.

*** At www.ecopiedra.com, in Data Sheets, see the sound reduction improvement Index for different construction solutions.

Quality Department

E. P. S.

E. P. S.


ECOPIEDRA, S.L.

IF-8/00



PRODUCT TECHNICAL DATA SHEET

TECHNICAL DATA SHEET NO.:10012002	DATE: 12.06.2008
MANUFACTURER: ECOPIEDRA, S.L	PRESENTATION: CAJA DE 0,6m ²
CITY: LOECHES	



DESIGNATION OF THE MODEL:	LAJA MARRÓN TIERRA STANDARD
MASS COLOURING:	MARRÓN TIERRA
THICKNESS:	Entre 25 y 55mm
NOMINAL DIMENSIONS:	300 X 100mm

TECHNICAL CHARACTERISTICS	TEST METHOD	VALUES GUARANTEED BY THE MANUFACTURER	TOLERANCES
Appearance and colour.			
Changes in design colour.	Visual	Not accepted	--
Changes in design appearance of the face.	Visual	Not accepted	--
Dimensional characteristics.			
Length of flat pieces.	UNE EN 14617-16	301,0	± 5 mm
Width of flat pieces.	UNE EN 14617-16	101,0	± 5 mm
Thickness of flat pieces.	UNE EN 14617-16	57,0	± 5 mm
Physical characteristics.			
Water absorption.	UNE EN 14617-1	12,5	12 ± 2 %
Apparent density.	UNE EN 14617-1	1700	Kg/m ³
Efflorescence*.	UNE 67029 ECO-PE-08	Non - Efflorescent	--
Mechanical characteristics.			
Durability (Frost susceptibility).	UNE EN 14617-5	Non – Frost Susceptibility (NFS)	--
Compressive strength.	UNE EN 1015-11	28,0	± 2 MPa
Flexural strength	UNE EN 14617-2 ECO-PE-10	6,2	± 1 MPa
Thermal shock resistance.	UNE EN 14617-6	No changes in appearance of the face	--
Adherence*.	UNE EN 1348	> 1,0	± 0,5 MPa
Adherence**.	UNE EN 1015-12	No applicable	--
TECHNICAL BUILDING CODE			
Fire resistance.	EN ISO 1716:02 EN ISO 1182:02	CLASE A1*	CLASE A1*
Acoustic insulation.	UNE EN ISO 140-3 UNE EN ISO 140-16	5 - 24	dB
Thermal resistance (R)		0,05-0,10	m ² .K/W
Thermal conductivity (λ)	UNE EN 12667:02	0,376	W/m. K
Transmittance (U)		20,00-10,00	W/m ² .K

* Adhesive Cement recommended by ECOPIEDRA, S.L.

** Mortar for Joints recommended by ECOPIEDRA, S.L.

*** At www.ecopiedra.com, in Data Sheets, see the sound reduction improvement Index for different construction solutions.

Quality Department

ECOPIEDRA, S.L.


IF-8/00



PRODUCT TECHNICAL DATA SHEET



TECHNICAL DATA SHEET NO.:10012002	DATE: 12.06.2008
MANUFACTURER: ECOPIEDRA, S.L	PRESENTATION: CAJA DE 0,6m ²
CITY: LOECHES	



DESIGNATION OF THE MODEL:	LAJA MARRÓN TIERRA STANDARD
MASS COLOURING:	MARRÓN TIERRA
THICKNESS:	Entre 25 y 55mm
NOMINAL DIMENSIONS:	500 X 100mm

TECHNICAL CHARACTERISTICS	TEST METHOD	VALUES GUARANTEED BY THE MANUFACTURER	TOLERANCES
Appearance and colour.			
Changes in design colour.	Visual	Not accepted	--
Changes in design appearance of the face.	Visual	Not accepted	--
Dimensional characteristics.			
Length of flat pieces.	UNE EN 14617-16	504,0	± 5 mm
Width of flat pieces.	UNE EN 14617-16	102,0	± 5 mm
Thickness of flat pieces.	UNE EN 14617-16	55,0	± 5 mm
Physical Characteristics.			
Water absorption.	UNE EN 14617-1	12,5	12 ± 2 %
Apparent density.	UNE EN 14617-1	1700	Kg/m ³
Efflorescence*.	UNE 67029 ECO-PE-08	Non - Efflorescent	--
Mechanical characteristics.			
Durability (Frost susceptibility).	UNE EN 14617-5	Non – Frost Susceptibility (NFS)	--
Compressive strength.	UNE EN 1015-11	28,0	± 2 Mpa
Flexural strength	UNE EN 14617-2 ECO-PE-10	6,2	± 1 MPa
Thermal shock resistance.	UNE EN 14617-6	No changes in appearance of the face	--
Adherence*.	UNE EN 1348	> 1,0	± 0,5 MPa
Adherence**.	UNE EN 1015-12	No applicable	--
TECHNICAL BUILDING CODE			
Fire resistance.	EN ISO 1716:02 EN ISO 1182:02	CLASE A1*	CLASE A1*
Acoustic insulation.	UNE EN ISO 140-3 UNE EN ISO 140-16	5 - 24	dB
Thermal resistance (R)	UNE EN 12667:02	0,05-0,10	m ² .K/W
Thermal conductivity (λ)		0,376	W/m. K
Transmittance (U)		20,00-10,00	W/m ² .K

* Adhesive Cement recommended by ECOPIEDRA, S.L.

** Mortar for Joints recommended by ECOPIEDRA, S.L.

*** At www.ecopiedra.com, in Data Sheets, see the sound reduction improvement Index for different construction solutions.

Quality Department

ECOPIEDRA, S.L.

IF-8/00